

ECOAMIDE™6G30-OM850A

Intertech Limited

<http://www.intertech.co.jp>

ECOAMIDE™6G30-OM850A

- ◆ Ecoamide™6G30-OM850A is a recycled 6PA, reinforced with 30% glass, black colored product.
- ◆ Ecoamide™6G30-OM850A has high mechanical properties, reliability and long term durability.
- ◆ Ecoamide™6G30-OM850A has been developed for applications that require beautiful surfaces without an expensive painting procedure after molding.
- ◆ Ecoamide™6G30-OM850A uses our original 10 μ diameter glass fibers that functions as an efficient reinforcement system in PA matrix.



Mechanical Properties of Ecoamide™6G30-OM850A

Grade	Glass	Polymer	Density	Shrinkage	Tensile Strength	Elongation	Flexural Modules	Izod Impact
Unit	%		Unit	%	MPa	%	MPa	J/m
Ecoamide 6G30-OM850A	30	6PA	1.36	0.5/0.8	185	3.5	9400	108



Contact us

- ◆ Intertech Limited
- ◆ Zip 123-0873
2-23-1 Ougi Adachi-Ku Tokyo, Japan
- ◆ URL <http://www.intertech.co.jp>
- ◆ Phone +81-3-5837-5550
- ◆ Fax +81-3-5837-5551
- ◆ E-mail itl@intertech.co.jp